

SAMPLING ASPHALT MATERIALS AASHTO T 40

APPARATUS

- ☐ Asphalt Material (except Emulsion)
 - ☐ Double friction-top can
 - ☐ Square can with screw top
 - ☐ Small mouth can with screw cap
- ☐ Emulsion
 - ☐ Widemouth jar made of glass or plastic
 - ☐ Bottle made of glass or plastic

SAMPLE LOCATION

- ☐ Bulk Storage Tank
 - ☐ Approved valve in tank
 - ☐ Approved valve in line
- ☐ Distributor
 - ☐ Approved sampling valve
- ☐ HMA Plant Storage Tank
 - ☐ Approved tank valve
- ☐ Transport
 - ☐ Approved sampling valve

SAMPLE SIZE

- ☐ Asphalt Materials (except Emulsions)
 - ☐ 1.0 qt
- ☐ Emulsions
 - ☐ 1/2 gal.

AASHTO T 40

PROCEDURE

- ☐ At least four quarts are drained from the valve before sample is obtained
- ☐ Containers are sealed with clean, dry, tight fitting lids
- ☐ Spilled material is wiped from container with a clean, dry cloth that has not been dipped in solvent
- ☐ Containers are labeled clearly with a wick labeling pen. Lids are not labeled.

NA - Not Applicable

X - Requires Corrective Action

√ - Satisfactory

Acceptance Technician

INDOT

Date

Comments _____

